


NON-WOVEN GEOTEXTILE

GE - 112



Project Reference:

SKAPS GE-112 is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPS GE-112 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2 to 13.



SKAPS GE-112 conforms to the Minimum Average Roll Values (MARV) listed below:

Property	Method	English (MARV ²)	Metric (MARV ²)
Weight	ASTM D 5261	12 oz/yd ²	407 g/m ²
Grab Tensile Strength	ASTM D 4632	330 lbs	1.47 kN
Grab Elongation	ASTM D 4632	50%	
Trapezoid Tear Strength	ASTM D 4533	125 lbs	0.556 kN
Thickness ⁴	ASTM D 5199	120 mils	3.05 mm
CBR Puncture Resistance	ASTM D 6241	900 lbs	4 kN
Permittivity ⁴	ASTM D 4491	0.90 sec ⁻¹	0.90 sec ⁻¹
Permeability ⁴	ASTM D 4491	0.30 cm/sec	0.30 cm/sec
Water Flow ⁴	ASTM D 4491	70 gpm/ft ²	2851 l/min/m ²
Apparent Opening Size (AOS) ^{3&4}	ASTM D 4751	100 US Sieve	0.15 mm
UV Resistance	ASTM D 4355	70%/500 hrs.	

Packaging

Roll Dimensions (W x L)	15 x 480 ft.	4.58 m x 146.30 m
Area Per Roll	800 sq. yards	670.05 sq. meters

Note

1. The property values listed above are subject to change without notice.
2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
3. Maximum Average Roll Value (MaxARV)
4. At time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.