

BIAXIAL GEOGRID**SKAPS BX1100**

Product Type: Integrally Formed Biaxial Geogrid

Polymer: Polypropylene

Index Properties	Test Method	UoM	MD x XMD Value ¹
Aperture Dimensions ²	Direct Measurement	mm (in)	25 x 33 (1.0 x 1.3)
Rib Thickness ²	Direct Measurement	mm (in)	0.76 x 0.76 (0.03 x 0.03)
Junction Thickness ²	Direct Measurement	mm (in)	2.80 x 2.80 (0.11 x 0.11)
Minimum True Initial Modulus in Use ³	ASTM D6637M	kN/m (lb/ft)	278 x 412 (19,057 x 28,246)
Tensile Strength @ 2% Strain ³	ASTM D6637M	kN/m (lb/ft)	4.1 x 6.6 (280 x 450)
Tensile Strength @ 5% Strain ³	ASTM D6637M	kN/m (lb/ft)	8.5 x 13.4 (580 x 920)
Ultimate Tensile Strength ³	ASTM D6637M	kN/m (lb/ft)	12.4 x 19.0 (850 x 1,300)
Structural Integrity	Test Method	UoM	Value ¹
Junction Efficiency ⁴	ASTM D7737/D6637	%	93
Flexural Stiffness ⁵	ASTM D7748	mg-cm	250,000
Aperture Stability ⁶	GRI-GG9	m-N/deg	0.32
Durability	Test Method	UoM	Value ¹
Resistance to Long-term Degradation ⁸	ASTM D6637	%	100
Resistance to UV Degradation ⁹	ASTM D4355	%	95

Packaging

Roll Dimensions (W x L)	150" x 328'
Area Per Roll	455.56 Square Yards

Note

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759
2. Nominal dimensions
3. Determined in accordance with ASTM D6637 Method A.
4. Load transfer capability determined in accordance with ASTM D7737.
5. Resistance to bending force determined in accordance with ASTM D7748/D7748M.
6. Resistance to in-plane rotational movement measured in accordance with ASTM D7864/D7864M.
inch specimen restrained at its perimeter in accordance with GRI GG9.
8. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
9. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355.

This information is provided for reference purposes only and is not intended as a warranty or guarantee.

SKAPS assumes no liability in connection with the use of this information.